


Magnet Specifications

300-01-025 NEO35H MATERIAL SPECS(25 °C):	TYPICAL:	MINIMUM:
PROCESSING TYPE:	SINTERED	
BR GAUSS:	12000	11700
HC OERSTED:	11500	11000
HCI OERSTED:		17000
BHMAX MGOE:	35	33
BR TEMP CO (%/°C):	-0.11	
RECOIL PERM. (UREC):		
TC CURIE TEMP (°C):	310	
MAX OPERATING TEMP (°C):	110	
Rev A PLATING, NICKEL:	0.0005"	0.0002"

FIELD STRENGTH CLOSE TO MAGNET



FIELD STRENGTH FAR FROM MAGNET

