


Magnet Specifications

300-01-051 NEO48		
MATERIAL SPECS(25°C):	TYPICAL:	MINIMUM:
PROCESSING TYPE:	SINTERED	
BR GAUSS:	13,900	13,600
HC OERSTED:	12,000	9,500
HCI OERSTED:	13,000	12,000
BHMAX MGOE:	48.0	45.0
BR TEMP CO (%/°C):	-.11	
RECOIL PERM. (UREC):	1.05	
TC CURIE TEMP (°C):	310	
MAX OPERATING TEMP (°C):	90	
Rev A		

FIELD STRENGTH CLOSE TO MAGNET



FIELD STRENGTH FAR FROM MAGNET

